

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2001-210508

(43)Date of publication of application : 03.08.2001

(21)Application number : 2000-196345 (71)Applicant : HITACHI METALS LTD

(22)Date of filing : 29.06.2000 (72)Inventor : TOKORO HISATO
UCHIDA KIMIO
ODA KAZUO
MIKAMOTO TSUKASA

(30)Priority

Priority number : 11190351	Priority date : 05.07.1999	Priority country : JP
11329590	19.11.1999	JP

(54) METHOD OF MANUFACTURING ARC SEGMENT MAGNET, RING MAGNET,
AND RARE EARTH SINTERED MAGNET

(57)Abstract:

PROBLEM TO BE SOLVED: To provide an R-T-B sintered magnet of high performance, having a thin film shape, a thin-walled shape, or radial anisotropy with an enhanced degree of orientation, in comparison with the conventional magnets.

SOLUTION: When the sum total of main contents of R, T, and B (R is at least one of rare earth elements including Y and T is Fe or Fe and Co) is 100% by weight %, the arc segment magnet comprises the sintered magnet, where R is 28-33%, B is 0.8-1.5%, and T is the rest, is characterized in that a quantity of oxygen contained inevitably in with respect to the total weight of the arc segment magnet is equal to or less than 0.3%, the thickness of the arc segment magnet has a thin-film shape of 1-4 mm, the density is higher than 7.56 Mg/m³ (g/cm³), and at room temperature, coercive force iH_c is equal to or more than 1.1 MA/m (14 kOe) and the degree of orientation ($Br/4\pi I_{max}$) in a given anisotropy direction is equal to or higher than 96%.

